

**PATENT APPLICATION**  
**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re application of

Takashi TAKEDA, et al.

Appln. No.: Unknown

Confirmation No.: Unknown

Group Art Unit: Unknown

Filed: January 29, 2002

Examiner: Unknown

For: PHOSPHOR

**PRELIMINARY AMENDMENT**

Commissioner for Patents  
Washington, D.C. 20231

Sir:

Prior to examination, please amend the above-identified application as follows:

**IN THE SPECIFICATION:**

Pages 4-5,

(Amended)

After mixing, the obtained mixture is calcined at a temperature in a range of approximately 900°C to 1100°C for approximately 1 to 100 hours, whereby a phosphor of the present invention can be obtained. In the case where substances that are decomposed at a high temperature thereby becoming oxides, such as hydroxides, carbonates, nitrates, halides, oxalates, etc. are used in materials, it is possible to pre-calcine the mixture at a temperature, for instance, in a range of approximately 600°C to 800°C before the main calcining.

20050129 012900

5/19  
P. 30.  
12/6/02

A,

Takashi TAKEDA et al.  
Q68254  
PRELIMINARY AMENDMENT

**REMARKS**

The specification has been amended to correct a trivial error. Entry and consideration of this Amendment is respectfully requested.

Respectfully submitted,



---

J. Frank Osha  
Registration No. 24,625

SUGHRUE MION, PLLC  
2100 Pennsylvania Avenue, N.W.  
Washington, D.C. 20037-3213  
Telephone: (202) 293-7060  
Facsimile: (202) 293-7860

Date: January 29, 2002

20020129 09:00:00

Takashi TAKEDA et al.  
Q68254  
PRELIMINARY AMENDMENT

## APPENDIX

### VERSION WITH MARKINGS TO SHOW CHANGES MADE

#### IN THE SPECIFICATION:

After mixing, the obtained mixture is calcined at a temperature in a range of approximately 900°C to 1100°C for ~~approximately 1 to 10 hours~~ approximately 1 to 100 hours, whereby a phosphor of the present invention can be obtained. In the case where substances that are decomposed at a high temperature thereby becoming oxides, such as hydroxides, carbonates, nitrates, halides, oxalates, etc. are used in materials, it is possible to pre-calcine the mixture at a temperature, for instance, in a range of approximately 600°C to 800°C before the main calcining.